

## **Technical Data Sheet**

## IFR 50/38x38/11x9 - Concave





## IFR - Isophtalic Fire Resistant

Туре:	Cast molded grating. ( $TWS = GRP = FRP = GFK$ )						
Material:	Isophtalic resin reinforced with fiberglass rovings						
Color:	Similar to the one specified in the RAL palette						
Chemical Resistance:	<ul> <li>According to the Merim chemical resistance chart</li> <li>Chemical resistance depends on the type of resin used</li> </ul>						
Tolerances:	- Length and width: +2 / -4 mm						
	- Height:	+2 / -2 mm					
	- Weight: 42 kg/m2	+/- 10%					
	- Warping:	< 10  mm / mb					
Structure:	- Mold	- high quality Isophtalic resin					
	- Surface	- Concave					
	- Resin content:	- about 60%					
	- Glass content:	- about 40%					
Fire Resistance:	- Self-extinguishing according to DIN EN 13501-1						
	- Classification in accordance with EN 13501-1 level Bfl-S1						
Anti Slip:	- Class: $>40\ ^{\circ}$ - R 13 according to BRG 181 and DIN 51130						
Other:	- Standard operating tem	perature range:	- 40 °C / + 80 °C				
	- Maximum operating ter - resistance to UV radiat	- 100 °C / + 155 °C					
	- Good electrical insulator - does not conduct electricity						

- Good thermal insulator - does not conduct heat

In accordance with the standards: EN ISO 14122-2: 2016 and DIN 24537-3, the following is adopted:

The minimum loads to be considered for walkways and working platforms are as follows:

- 2.0 kN / m2 with a uniform load on the structure;

- 1.5 kN with a concentrated load applied in the most unfavorable place

on a floor area of 200 mm x 200 mm.

The deflection of the floor surface after applying the load assumed in the design should not be greater than L/200 of the span of the supports.

The difference in height between the loaded floor surface and the adjacent unloaded floor surface should not exceed 4 mm.

If the deflection is L/200>4mm, it is recommended to use a connector.

According to BGI / GUV-I 588-1, the minimum support of the grating should be equal to the height of the grating, but not less than 30 mm.

Support spacing [L]	300	400	500	600	700	800	900	1000	1100
Fv	2,00	2,00	2,00	2,00	2,00	2,00	2,00	2,00	2,00
fv	0,03	0,06	0,09	0,12	0,31	0,49	0,68	0,95	1,56
Fp	1,50	1,50	1,50	1,50	1,50	1,50	1,50	1,50	1,50
fp	0,09	0,18	0,27	0,36	0,74	1,12	1,50	1,95	2,40
L/200	1,50	2,00	2,50	3,00	3,50	4,00	4,50	5,00	5,50
Support spacing [L]	1200	1300	1400	1500	1600	1700	1800	1900	2000
Fv	2,00	2,00	2,00	2,00	2,00	2,00	2,00	2,00	2,00
fv	2,16	2,77	3,37	3,98	5,41	6,84	8,27	9,70	11,13
Fp	1,50	1,50	1,50	1,50	1,50	1,50	1,50	1,50	1,50
fp	2,85	3,30	3,75	6,08	7,72	9,36	10,99	12,63	14,27
L/200	6,00	6,50	7,00	7,50	8,00	8,50	9,00	9,50	10,00
$Fv - 2 kN/m^2$ of uniform load on the structure $Fn - 1 5kN$ concentrated load on the surface of 200x200 mm						Compliant with L/200			

Load capacity table of the gratings (100 kg  $\approx$  1 kN):

Fv - 2 kN/m2 of uniform load on the structure

Fp - 1.5kN concentrated load on the surface of 200x200 mm

fv - deflection for "Fv" load [mm]

Does not comply with L/200

## The method of calculating the surface of gratings:

fp - deflection for "Fp" load [mm]



\* - Product Technical Data Sheet may be changed without prior notice.

This document and the information it contains are based on data believed to be reliable, however factors such as environmental changes, application or installation, changes to operating procedures or data extrapolation may produce different results.